

: 60x60 Nidus Bianco Rec. Name of The Product **Production Facility** : Glazed Porcelain Factory

: Dry-pressed ceramic tiles / Group Bla / GL : Interior & exterior floor **Product Group** 

: Mat

Recommended Use General Properties Report Date : 21.11.2023

Test Title	Test Results	Requirements	Desicion	
Length & Width (mm)	597 x 597 mm	596,5 – 597,5 mm	OK	
Thickness (mm)	7,0 mm	6,7 – 7,3 mm	OK	
Straightness of Sides (%)	± %0,2	± %0,5	OK	
Rectangularity (%)	± %0,2	± %0,6	OK	
Edge Curvature (%)	± %0,2	± %0,5	OK	
Corner Curvature (%)	± %0,2	± %0,5	OK	
Center Curvature (%)	± %0,2	± %0,5	OK	
Small Colour Differences	First Quality	> %95 perfect	OK	
Water Absorption	< 0,1 %	≤ <b>0</b> , <b>5</b> %	OK	
Breaking Strength (N)	> 1300N	> 700N	OK	
Modulus of Rupture (N/mm²)	>46 N/mm <sup>2</sup>	> 35 N/mm <sup>2</sup>	OK	
Abrasion Resistance (PEI)	V	As declared	OK	
Coeff. Of Thermal Expansion	< 7,0 x 10 <sup>-6</sup>	As declared	OK	
Thermal Shock Resistance	Resistant	Required	OK	
Crazing Resistance	Resistant	Required	OK	
Frost Resistance	Resistant	Required	OK	
Coefficient of Friction (μ)	~62,0	As declared	OK	
Moisture Expansion (mm/m)	< 0,3	As declared	OK	
Impact Resistance	Resistant	As declared	OK	
Staining Resistance	Class 5	Min. Class 3	OK	
Resistance to low conc. of Acid & Alkalis	Α	As declared	OK	
Resistance to high conc. of Acid & Alkalis	Α	As declared	OK	
Household Chemicals	Α	Min. B	OK	
Release of Cadmium	< 0,07 mg/dm²	As declared	OK	
Release of Lead	< 0;8 mg/dm²	As declared	OK	
OVERALL RESULT	All test results are posit	test results are positive according to the norms of		
	ISO 13006 and EN 14411 standards, Annex G.			

<u>Prepared by</u> Kağan Kurnaz Quality Assurance Staff

Approved by Ahmet Pehlivan Quality Assurance Manager