


**Name of The Product** : 30x90 Cappadocia Grey Dekofon Rec.  
**Production Facility** : Wall Tile Factory  
**Product Group** : Dry-pressed ceramic tiles / Group BIII / GL  
**Recommended Use** : Interior walls  
**General Properties** : Mat  
**Report Date** : 25.07.2022

Test Title	Test Results	Requirements	Desicion
Length & Width (mm)	300,0 x 900,0	299,8 – 300,2 899,8 – 900,2	OK
Thickness (mm)	8,0 mm	7,8 – 8,2 mm	OK
Straightness of Sides (%)	± %0,2	± %0,5	OK
Rectangularity (%)	± %0,2	± %0,6	OK
Edge Curvature (%)	± %0,2	± %0,5	OK
Corner Curvature (%)	± %0,2	± %0,5	OK
Center Curvature (%)	± %0,2	± %0,5	OK
Small Colour Differences	First Quality	> %95 perfect	OK
Water Absorption	>13 % - <15 %	10 % < E ≤ 20 %	OK
Breaking Strength (N)	> 800 N	> 600 N	OK
Modulus of Rupture (N/mm <sup>2</sup> )	> 20 N/mm <sup>2</sup>	> 15 N/mm <sup>2</sup>	OK
Coeff. Of Thermal Expansion	< 7,0 x 10 <sup>-6</sup>	As declared	OK
Thermal Shock Resistance	Resistant	Required	OK
Crazing Resistance	Resistant	Required	OK
Frost Resistance	Resistant	Required	OK
Coefficient of Friction (μ)	~62,0	As declared	OK
Moisture Expansion (mm/m)	< 0,3	As declared	OK
Impact Resistance	Resistant	As declared	OK
Staining Resistance	Class 5	Min. Class 3	OK
Resistance to low conc. of Acid & Alkalis	B	As declared	OK
Resistance to high conc. of Acid & Alkalis	B	As declared	OK
Household Chemicals	A	Min. B	OK
Release of Cadmium	< 0,07 mg/dm <sup>2</sup>	As declared	OK
Release of Lead	< 0;8 mg/dm <sup>2</sup>	As declared	OK
OVERALL RESULT	All test results are positive according to the norms of ISO 13006 and EN 14411 standards, Annex L.		

**Prepared by**  
Furkan Taşdelen  
Quality Assurance Staff



**Approved by**  
Ahmet Pehlivan  
Quality Assurance Manager

